

## Clay 1752

---

**Chemical analysis:**

SiO <sub>2</sub>	74.7 %
Al <sub>2</sub> O <sub>3</sub>	19.6 %
TiO <sub>2</sub>	1.4 %
Fe <sub>2</sub> O <sub>3</sub>	1.1 %
CaO	<0.1 %
MgO	0.4 %
K <sub>2</sub> O	2.6 %
Na <sub>2</sub> O	<0.1 %

**Firing colour:**

light

**Firing temperature:**

1070°C

1200 °C

**Firing shrinkage %:**

1.9

5.4

Sieve residue in % > 63 µm

4.0

Sieve residue in % > 180 µm

0.6