

Kaolin KE

Chemical analysis:

SiO ₂	73.8 %
Al ₂ O ₃	19.7 %
TiO ₂	1.1 %
Fe ₂ O ₃	4.2 %
CaO	<0.1 %
MgO	0.4 %
K ₂ O	3.7 %
Na ₂ O	<0.1 %

Firing colour:

light

Firing temperature:

1070°C

1200 °C

Firing shrinkage %:

0.7

4.8