

Kaolin KR 30

Chemical analysis:

SiO ₂	71.2 %
Al ₂ O ₃	18.2 %
TiO ₂	1.1 %
Fe ₂ O ₃	5.1 %
CaO	<0.1 %
MgO	0.7 %
K ₂ O	3.5 %
Na ₂ O	<0.1 %

Firing colour:

red

Firing temperature:

1070°C

1200 °C

Firing shrinkage %:

0.6

6.3