

## Clay 3616

---

**Chemical analysis:**

SiO <sub>2</sub>	61.3 %
Al <sub>2</sub> O <sub>3</sub>	32.4 %
TiO <sub>2</sub>	1.9 %
Fe <sub>2</sub> O <sub>3</sub>	1.6 %
CaO	0.2 %
MgO	0.4 %
K <sub>2</sub> O	2.0 %
Na <sub>2</sub> O	<0.07 %

**Ceramic data:**

<b>Firing temperature:</b>	1070 °C	1200 °C
Firing colour:	light	light
Firing shrinkage %:	6	11